

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

ecoSHIELD* Eco Latex PF 250



0120

EN374:2003



LEVEL 3

EN374:2003



- Category III PPE glove (PPE Directive 89/686/EEC)
- Complex Design - For mortal and irreversible risks
- Powder-free natural latex glove
- Ambidextrous
- 250 mm / 0.12 mm (EN 420:2003 + A1:2009)
- AQL 0.65 (EN 374-2:2014 Level 3)
- Viral penetration test (ISO 16604:2004 Procedure B & ASTM F1671-97b)
- Waterproof and for low chemical protection
- Tested for chemical permeation (EN 16523-1:2015 supersedes EN 374-3:2003)
- Type I hypersensitivity & type IV hypersensitivity reduced

7664-93-9
Sulphuric Acid 50%

LEVEL 6
480 min

7681-52-9
Sodium Hypochlorite 13%

LEVEL 6
480 min

1310-73-2
Sodium Hydroxide, 50%

LEVEL 6
480 min

1239-45-8
Ethidium Bromide 5%

LEVEL 6
480 min

7647-01-0
Hydrochloric Acid 37%

LEVEL 2
57 min

79-06-1
Acrylamide 40%

LEVEL 6
480 min

7664-93-9
Sulphuric Acid 95%-98%

LEVEL 1
18 min

67-63-0 Isopropanol 70%	LEVEL 1 11 min
64-17-5 Ethanol 70%	LEVEL 0 9 min
64-19-7 Acetic Acid 100%	LEVEL 0 3 min
67-64-1 Acetone 99,8%	LEVEL 0 1 min
1330-20-7 Xylene 98,5%	LEVEL 0 1 min
1336-21-6 Ammonium Hydroxide 25%	LEVEL 0 7 min
75-05-8 Acetonitrile 99,9%	LEVEL 0 2 min
80-62-6 Methyl Methacrylate 99%	LEVEL 0 0 min
75-09-2 Dichloromethane 99%	LEVEL 0 0 min
67-56-1 Methanol 99,9%	LEVEL 0 0 min
107-13-1 Acrylonitrile 99%	LEVEL 0 1 min