



Class: EN ISO 20345:2011 S3 SRC Sizes: 38-48 Instep: 12 Weight(±10%): 635 gr. (\*)

## **TECHNICAL SHEET ART. FALCON**

**Description** Low shoe in black Safety-Nubuk with padded storm-cuff, 100% polyester lining, Non-Metallic HRP Insole , ATOMIC Insole, double density polyurethane sole , bending resistant , abrasion resistant , oil resistant , slip resistant , ESD.

**Plus** Midsole compound particularly studied to get a soft PU density for a higher comfort **Suggested sectors of usage** Building/Construction, Mechanical Industry, Professional / Craftsman , Farming/Zootechnics

**Care and Maintenance** clean periodically the outsole and the upper with non aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source.



Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirements
<b>Toe Cap</b> : Non-Metallic TOP COMPOSITE toe cap, impact resistant 200 J	5.3.2.3	Impact resistance	mm	14,5	≥14
	5.3.2.4	Compression resistance	mm	16,0	≥ 14
<b>Midsole:</b> non metallic HRP Insole with high tenacity fibres layers, ceramized and treated with plasma	6.2.1.1	Perforation resistance	N	1.100 without holes	≥ 1.100
<b>ESD footwear</b> : dissipation capacity of the electrostatic charge	EN ISO	Resistance to floor			
	613 <del>4</del> 0	(footwear/floor resistance)	Ohm	4,67 x 10 <sup>7</sup>	$<$ 1,00 x $10^{8} \Omega$
	5-1:2016	Transverse resistance of the sole	Ohm	$3,20 \times 10^7$	$\leq$ 1,00 x $10^8 \Omega$
		Chargeability	V	< 78 V	< 100 V
Capacity of Energy Absorption in the heel area	6.2.4	Energy absorption in the heel area	J	24,0	≥ 20
Upper: Black Safety-Nubuk	5.4.6	Water vapour permeability	mg/cm <sup>2</sup> h	5,4	≥ 0,8
		Coefficient of permeability	mg/cm <sup>2</sup>	49,1	≥ 15
	5.4.3	Tearing Strength	N	65	≥ 60
	6.3	Water absorption	%	18	≤ 30
		Water penetration	g	0,1	≤ 0,2
<b>Vamp Lining</b> : honeycomb finished polyester, breathable, abrasion resistant, black	5.5.3	Water vapour permeability	mg/cm <sup>2</sup> h	6,8	≥ 2
colour		Coefficient of permeability	mg/cm <sup>2</sup>	54,4	≥ 20
	5.5.1	Tearing Strength	N	25	≥ 15
	5.5.2	Abrasion resistance (dry)	cycles	no rupture	25.600
		Abrasion resistance (wet)	cycles	no rupture	12.800
<b>Quarter Lining</b> : honeycomb finished polyester, breathable, abrasion resistant, green fluo colour	5.5.3	Water vapour permeability	mg/cm <sup>2</sup> h	6,1	≥ 2
		Coefficient of permeability	mg/cm <sup>2</sup>	54,0	≥ 20
	5.5.1	Tearing Strength	N	25	≥ 15
	5.5.2	Abrasion resistance (dry)	cycles	no rupture	51.200
		Abrasion resistance (wet)	cycles	no rupture	25.600
Insole lining: textile anti perforation midsole HRP insole	5.7.3	Water Absorption	mg/cm <sup>2</sup>	76	≥ 70
		Ability to release water		99%	≥ 80%
<b>Sole</b> : double density polyurethane , bending resistant, abrasion resistant, oil	5.8.2	Tearing Strength	kN/m	8,5	≥ 8
resistant, slip resistant, ESD	5.8.3	Abrasion resistance	mm³	144	≤ 150
	5.8.4	Bending resistance	mm	1,5	≤ 4
	5.8.5	Hydrolysis	mm	2	≤ 6
	6.4.2	Hydrocarbons resistance (volume increase)	%	1,0%	≤ 12%
	5.11	Slip resistance on ceramic floor with water and	flat	0,47	≥ 0,32
advancod		detergent	inclined	0,32	≥ 0,28
advanced		Slip resistance on steel floor with glycerine	flat	0,24	≥ 0,18
SAFETY			inclined	0,22	≥ 0,13

Golf style and its components: no presence of dangerous substances by Annex VII to regulation no. 1907/2006/CE and subsequent amendments and additions  $^{(*)}$  = Indicative weight that refers to  $\frac{1}{2}$  pair in size 42